



**060EG0075115PT**

**Item #: S7075060**

60# ENCORE HI GLOSS/751 PERMANENT ADHESIVE/1.5 MIL C1 PET LINR WSIL

Approximate weight per MMSI: 229 lbs. Standard core size is 3 inches. Total caliper: 5.02 mils +/- 10%

**FACESTOCK**

61# (89 g/m<sup>2</sup>) super calendered high-gloss sheet. This C1S paper is designed for premium labeling applications.

Non-cast coated paper featuring excellent gloss and suitable for process printing.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500	60.8	grams/sq meter	90.0	TAPPI T410
Caliper - Average	mil	2.9	um (micrometer)	73.7	TAPPI T411
Gloss - Wire Side	% @ 75 degrees	89	%	89.0	TAPPI T480
Opacity	%	87	%	87.0	TAPPI T425
Smoothness (PPS) Print Side	um	1	um	1.0	TAPPI T555
Smoothness (PPS) - Back Side	um	2.7	um	2.7	TAPPI T555
Wet Tear-MD	grams	47	mN		TAPPI T491/414
Wet Tear-CD	grams	50	mN		TAPPI T491/414
Tensile-MD	lb/inch	31.2	kN/m	5.5	TAPPI T494
Tensile-CD	lb/inch	17.9	kN/m	3.1	TAPPI T494
Brightness	%	92	%	92.0	TAPPI T452

**ADHESIVE**

A tackified acrylic with good adhesion to many substrates. Excellent die-cutting and stripping on wide web VIP applications. Good mandrel hold.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	18.7	
Shear (1 x 1/2 x 1 kg)	hours	18.0	hours	18.0	CPD-55
Peel - 180 D SS 20 min	lb/inch	2.1	grams/25 mm	937.5	CPD-52
Loop Tack Stain Steel	oz/sq inch	52	kg/645 sq mm	1.5	CPD-16
Loop Tack Glass	oz/sq inch	60	kg/645 sq mm	1.7	CPD-16
Min. App. Temp.	F	45	C	7	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

**LINER**

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.42	um (micrometers)	36.1	ASTM D374
Tensile Film - MD	lb/sq inch	32000	kg/sq cm	2249.6	ASTM D882
Tensile Film - TD	lb/sq inch	32000	kg/sq cm	2249.6	ASTM D882
Elongation at Break - MD	%	110	%	110.0	ASTM D882
Elongation at Break - TD	%	110	%	110.0	ASTM D882
Haze	%	6.5	%	6.5	ASTM D1003
Shrinkage-MD	% 30 min @ 302 F	1.5	% 30 min @ 150 C	1.5	ISO 2469
Shrinkage-TD	% 30 min @ 302 F	.4	% 30 min @ 150 C	.4	ISO 2469
Area Yield	sq in/lb	13968	sq m/kg	20.0	ASTM E252

Issued: 05/26/17

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions (found in the current Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book) in effect at the time of the sale shall control.

*La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho. Los Términos y Condiciones vigentes que regulan toda relación comercial de Green Bay Packaging Inc. - Coated Products Operations son los que se encuentran impresos en inglés en el último Libro de Precios. (Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book.)*

SPECIALISTS IN COATED SELF-ADHESIVE MATERIALS

ESPECIALISTAS EN MATERIALES AUTO-ADHESIVOS

3250 South Ridge Road • P. O. Box 19017 • Green Bay, WI 54307-9017 • USA

Phone: 001-(920)-337-1800, 800-445-4269, WI: 800-472-4442 • FAX: 001-(920)-337-1797, 800-705-0111