



020MY0010350SC

Item #: S7855152

2 ML CLEAR TC PET/103 PERMANENT ADHESIVE/3.2 ML WHITE KRAFT LINER
Approximate weight per MMSI: 255 lbs. Standard core size is 3 inches. Total caliper: 5.9 mils +/- 10%

FACESTOCK

A very clear, top coated polyester film. Top coating allows for printing with most standard flexo and UV letterpress inks.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	2.0	um (micrometers)	50.8	ASTM D374
Tensile Film - MD	lb/sq inch	35,000	kg/sq cm	2460.5	ASTM D882
Tensile Film - TD	lb/sq inch	35,000	kg/sq cm	2460.5	ASTM D882
Elongation at Break - MD	%	150	%	150.0	ASTM D882
Elongation at Break - TD	%	110	%	110.0	ASTM D882
Haze	%	.7	%	.7	ASTM D1003
Dim. Stability - MD	% @ 275 F	1.0	% @ 135 C	1.0	ASTM D1204
Dim. Stability - TD	% @ 275 F	1.0	% @ 135 C	1.0	ASTM D1204
Area Yield	sq in/lb	9922	sq m/kg	14.2	ASTM D4321

ADHESIVE

A high performance prime label acrylic adhesive with excellent clarity and adhesion to low energy surfaces, along with outstanding wet-out.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	16.6	
Shear (1 x 1/2 x 1 kg)	hours	2.4	hours	2.4	CPD-55
Peel - 180 D SS 20 min	lb/inch	2.3	grams/25 mm	1026.8	CPD-52
Loop Tack Stain Steel	oz/sq inch	50	kg/645 sq mm	1.4	CPD-16
Min. App. Temp.	F	40	C	4	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

LINER

A white densified kraft sheet 53# (86 g/m²) with excellent point-to-point caliper control.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500	54.5	grams/sq meter	88.8	TAPPI T410
Caliper - Average	mil	3.2	um (micrometer)	81.3	TAPPI T411
Opacity	%	72	%	72.0	TAPPI T425
Tear-MD	grams	42	mN	411.9	TAPPI T414
Tear-CD	grams	44	mN	431.5	TAPPI T414
Tensile-MD	lb/inch	49	kN/m	8.6	TAPPI T494
Tensile-CD	lb/inch	22	kN/m	3.9	TAPPI T494

Issued: 05/25/17

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions (found in the current Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book) in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho. Los Términos y Condiciones vigentes que regulan toda relación comercial de Green Bay Packaging Inc. - Coated Products Operations son los que se encuentran impresos en inglés en el último Libro de Precios. (Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book.)