



56H70758M40SC0758M40SC

Item #: S8265860

LOTS O DOTS HOLOGRM PPR/758M PERMANENT ADHESIVE/40 SC LINER/758M PERMANENT ADHESIVE/40 SC LINER

Approximate weight per MMSI: 371 lbs. Standard core size is 3 inches. Total caliper: 9.4 mils +/- 10%

FACESTOCK

60# (89 g/m²) decorative prismatic diffraction paper. Shim lines/seams are present in holographic material. This gap in the pattern will be up to 1/32" wide. The area between the shim lines measures 30" machine direction (MD) and 48" cross direction (CD)

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|-------------------|---------------|---------------|-----------------|--------------|-------------|
| Basis Weight | lbs/25X38-500 | 60.1 | grams/sq meter | 88.9 | TAPPI T410 |
| Caliper - Average | mil | 3.2 | um (micrometer) | 81.3 | TAPPI T411 |
| Moisture | % | 3.5 | % | 3.5 | TAPPI T412 |
| Tear-MD | grams | 44 | mN | 431.5 | TAPPI T414 |
| Tear-CD | grams | 52 | mN | 509.9 | TAPPI T414 |
| Tensile-MD | lb/inch | 29 | kN/m | 5.1 | TAPPI T494 |
| Tensile-CD | lb/inch | 12 | kN/m | 2.1 | TAPPI T494 |
| Stiffness-MD | Gurley (mg) | 112 | mN | 1.1 | TAPPI T543 |
| Stiffness-CD | Gurley (mg) | 64 | mN | .6 | TAPPI T543 |

ADHESIVE

A tackified acrylic general purpose permanent with great die-cutting and stripping properties, even on wide web applications. Excellent adhesion to many substrates, especially corrugated.

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|--------------------------------|------------|---------------|----------------|--------------|-------------|
| Caliper - Calculated | mils | 0.7 | um(micrometer) | 17.3 | |
| Shear (1 x 1/2 x 1 kg) | hours | 1.3 | hours | 1.3 | CPD-55 |
| Peel - 180 D SS 20 min | lb/inch | 1.582 | grams/25 mm | 706.3 | CPD-52 |
| Peel - 180 D HDPE 20 min | lb/inch | 1.4 | grams/25 mm | 625.0 | CPD-52 |
| Peel - 180 D LDPE 20 min | lb/inch | 1.318 | grams/25 mm | 588.4 | CPD-52 |
| Peel - 180 D Glass 20 min | lb/inch | 1.676 | grams/25 mm | 748.3 | CPD-52 |
| Peel - 180 D Corrugated 20 min | lb/inch | .83 | grams/25 mm | 370.6 | CPD-52 |
| Loop Tack Stain Steel | oz/sq inch | 38 | kg/645 sq mm | 1.1 | CPD-16 |
| Loop Tack HDPE | oz/sq inch | 23 | kg/645 sq mm | .6 | CPD-16 |
| Loop Tack LDPE | oz/sq inch | 20 | kg/645 sq mm | .6 | CPD-16 |
| Loop Tack Corrugated | oz/sq inch | 14 | kg/645 sq mm | .4 | CPD-16 |
| Loop Tack Glass | oz/sq inch | 35 | kg/645 sq mm | 1.0 | CPD-16 |
| Min. App. Temp. | F | 35 | C | 2 | |
| Service Temp. | F | -65 TO 200 | C | -54 TO 93 | |
| FDA Compliance | 21 CFR | 175.105 | | | |

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions (found in the current Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book) in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho. Los Términos y Condiciones vigentes que regulan toda relación comercial de Green Bay Packaging Inc. - Coated Products Operations son los que se encuentran impresos en inglés en el último Libro de Precios. (Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book.)

SPECIALISTS IN COATED SELF-ADHESIVE MATERIALS

ESPECIALISTAS EN MATERIALES AUTO-ADHESIVOS

3250 South Ridge Road • P. O. Box 19017 • Green Bay, WI 54307-9017 • USA

Phone: 001-(920)-337-1800, 800-445-4269, WI: 800-472-4442 • FAX: 001-(920)-337-1797, 800-705-0111



LINER

A white densified kraft sheet 41# (67 g/m²) with excellent point-to-point caliper control.

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|-------------------|----------------|---------------|-----------------|--------------|-------------|
| Basis Weight | lbs/24X36-500 | 41 | grams/sq meter | 66.8 | TAPPI T410 |
| Caliper - Average | mil | 2.4 | um (micrometer) | 61.0 | TAPPI T411 |
| Gloss | % @ 75 degrees | 57 | % @ 75 degrees | 57.0 | TAPPI T480 |
| Opacity | % | 60 | % | 60.0 | TAPPI T425 |
| Tear-MD | grams | 35 | mN | 343.2 | TAPPI T414 |
| Tear-CD | grams | 39 | mN | 382.5 | TAPPI T414 |
| Tensile-MD | lb/inch | 40 | kN/m | 7.0 | TAPPI T494 |
| Tensile-CD | lb/inch | 17 | kN/m | 3.0 | TAPPI T494 |
| Brightness | % | 76 | % | | TAPPI T452 |

ADHESIVE

A tackified acrylic general purpose permanent with great die-cutting and stripping properties, even on wide web applications. Excellent adhesion to many substrates, especially corrugated.

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|--------------------------------|------------|---------------|----------------|--------------|-------------|
| Caliper - Calculated | mils | 0.7 | um(micrometer) | 17.3 | |
| Shear (1 x 1/2 x 1 kg) | hours | 1.3 | hours | 1.3 | CPD-55 |
| Peel - 180 D SS 20 min | lb/inch | 1.582 | grams/25 mm | 706.3 | CPD-52 |
| Peel - 180 D HDPE 20 min | lb/inch | 1.4 | grams/25 mm | 625.0 | CPD-52 |
| Peel - 180 D LDPE 20 min | lb/inch | 1.318 | grams/25 mm | 588.4 | CPD-52 |
| Peel - 180 D Glass 20 min | lb/inch | 1.676 | grams/25 mm | 748.3 | CPD-52 |
| Peel - 180 D Corrugated 20 min | lb/inch | .83 | grams/25 mm | 370.6 | CPD-52 |
| Loop Tack Stain Steel | oz/sq inch | 38 | kg/645 sq mm | 1.1 | CPD-16 |
| Loop Tack HDPE | oz/sq inch | 23 | kg/645 sq mm | .6 | CPD-16 |
| Loop Tack LDPE | oz/sq inch | 20 | kg/645 sq mm | .6 | CPD-16 |
| Loop Tack Corrugated | oz/sq inch | 14 | kg/645 sq mm | .4 | CPD-16 |
| Loop Tack Glass | oz/sq inch | 35 | kg/645 sq mm | 1.0 | CPD-16 |
| Min. App. Temp. | F | 35 | C | 2 | |
| Service Temp. | F | -65 TO 200 | C | -54 TO 93 | |
| FDA Compliance | 21 CFR | 175.105 | | | |

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions (found in the current Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book) in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho. Los Términos y Condiciones vigentes que regulan toda relación comercial de Green Bay Packaging Inc. - Coated Products Operations son los que se encuentran impresos en inglés en el último Libro de Precios. (Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book.)

SPECIALISTS IN COATED SELF-ADHESIVE MATERIALS

ESPECIALISTAS EN MATERIALES AUTO-ADHESIVOS

3250 South Ridge Road • P. O. Box 19017 • Green Bay, WI 54307-9017 • USA

Phone: 001-(920)-337-1800, 800-445-4269, WI: 800-472-4442 • FAX: 001-(920)-337-1797, 800-705-0111



LINER

A white densified kraft sheet 41# (67 g/m²) with excellent point-to-point caliper control.

| Test Property | Units | Typical Value | Metric Units | Metric Value | Test Method |
|-------------------|----------------|---------------|-----------------|--------------|-------------|
| Basis Weight | lbs/24X36-500 | 41 | grams/sq meter | 66.8 | TAPPI T410 |
| Caliper - Average | mil | 2.4 | um (micrometer) | 61.0 | TAPPI T411 |
| Gloss | % @ 75 degrees | 57 | % @ 75 degrees | 57.0 | TAPPI T480 |
| Opacity | % | 60 | % | 60.0 | TAPPI T425 |
| Tear-MD | grams | 35 | mN | 343.2 | TAPPI T414 |
| Tear-CD | grams | 39 | mN | 382.5 | TAPPI T414 |
| Tensile-MD | lb/inch | 40 | kN/m | 7.0 | TAPPI T494 |
| Tensile-CD | lb/inch | 17 | kN/m | 3.0 | TAPPI T494 |
| Brightness | % | 76 | % | | TAPPI T452 |

Issued: 06/22/18

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions (found in the current Green Bay Packaging Inc. – Coated Products Operations, Roll Printer Price Book) in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho. Los Términos y Condiciones vigentes que regulan toda relación comercial de Green Bay Packaging Inc. – Coated Products Operations son los que se encuentran impresos en inglés en el último Libro de Precios. (Green Bay Packaging Inc. – Coated Products Operations, Roll Printer Price Book.)

SPECIALISTS IN COATED SELF-ADHESIVE MATERIALS

ESPECIALISTAS EN MATERIALES AUTO-ADHESIVOS

3250 South Ridge Road • P. O. Box 19017 • Green Bay, WI 54307-9017 • USA

Phone: 001-(920)-337-1800, 800-445-4269, WI: 800-472-4442 • FAX: 001-(920)-337-1797, 800-705-0111