



024TL0010292NB

Item #: S8276460

2.4 MIL WHITE BOPP/102 PERMANENT ADHESIVE/92 GA SIL CTD PET LINER

Approximate weight per MMSI: 139 lbs. Standard core size is 6 inches. Total caliper: 4.02 mils +/- 10%

FACESTOCK

A 2.4 mil glossy white BOPP top coated for ink adhesion. Has a distinctive pearlescent sheen. Excellent compatibility with UV curing inks and water based flexo ink systems. Label-Lyte is a Trademark of Jindal Films America.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	2.400	um (micrometers)	61.0	ASTM D374
Gloss - Films	% @ 45 degress	58	% @ 45 degrees	58.0	ASTM D2457
Opacity - Films	%	88	%	88.0	ASTM D589
Tensile Film - MD	lb/sq inch	12,900	kg/sq cm	906.9	ASTM D882
Tensile Film - TD	lb/sq inch	31,000	kg/sq cm	2179.3	ASTM D882
Stiffness-MD	Gurley (mg)	17	mN	.2	TAPPI T543
Stiffness-CD	Gurley (mg)	36	mN	.4	TAPPI T543
Elongation at Break - MD	%	150	%	150.0	ASTM D882
Elongation at Break - TD	%	43	%	43.0	ASTM D882
Dim. Stability - MD	% @ 275 F	-4.6	% @ 135 C	-4.6	ASTM D1204
Dim. Stability - TD	% @ 275 F	4.6	% @ 135 C	4.6	ASTM D1204
Area Yield	sq in/lb	15,400	sq m/kg	22.0	ASTM E252

ADHESIVE

A clear, water-resistant acrylic emulsion film adhesive, with high peel and tack, which adheres to a wide variety of surfaces, is blush resistant, and offers good wet-out.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	17.3	
Shear (1 x 1/2 x 1 kg)	hours	5.9	hours	5.9	CPD-55
Peel - 180 D SS 20 min	lb/inch	1.8	grams/25 mm	803.6	CPD-52
Loop Tack Stain Steel	oz/sq inch	38	kg/645 sq mm	1.1	CPD-16
Min. App. Temp.	F	40	C	4	
Service Temp.	F	-40 TO 160	C	-40 TO 71	
FDA Compliance	21 CFR	175.105			

LINER

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application. The benefits of this thinner gauge liner include reducing plastic use, decreasing shipping weight, and allowing more labels on a roll.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	.92	um (micrometers)	23.4	ASTM D374
Tensile Film - MD	lb/sq inch	32000	kg/sq cm	2249.6	ASTM D882
Tensile Film - TD	lb/sq inch	32000	kg/sq cm	2249.6	ASTM D882
Elongation at Break - MD	%	130	%	130.0	ASTM D882
Elongation at Break - TD	%	100	%	100.0	ASTM D882
Shrinkage-MD	% 30 min @ 302 F	1.5	% 30 min @ 150 C	1.5	ISO 2469
Shrinkage-TD	% 30 min @ 302 F	.4	% 30 min @ 150 C	.4	ISO 2469
Area Yield	sq in/lb	19800	sq m/kg	28.3	ASTM E252

Issued: 02/22/19

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions (found in the current Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book) in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho. Los Términos y Condiciones vigentes que regulan toda relación comercial de Green Bay Packaging Inc. - Coated Products Operations son los que se encuentran impresos en inglés en el último Libro de Precios. (Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book.)

SPECIALISTS IN COATED SELF-ADHESIVE MATERIALS

ESPECIALISTAS EN MATERIALES AUTO-ADHESIVOS

3250 South Ridge Road • P. O. Box 19017 • Green Bay, WI 54307-9017 • USA

Phone: 001-(920)-337-1800, 800-445-4269, WI: 800-472-4442 • FAX: 001-(920)-337-1797, 800-705-0111