



06INK0027840SC

Item #: S8821260

60# MATTE COATED INKJET/278 ULTRA REMOVABLE ADH/40 SC LINER

Approximate weight per MMSI: 240 lbs. Standard core size is 3 inches. Total caliper: 7.1 mils +/- 10%

FACESTOCK

A 60# (88 g/m²) matte-coated, acid-free, inkjet sheet with an exceptionally bright, blue-white shade. It provides high resolution imaging, and excellent smear and water resistance. It is compatible with a broad array of inkjet printers.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500	59.5	grams/sq meter	88.1	TAPPI T410
Caliper - Average	mil	4.3	um (micrometer)	110	TAPPI T411
Opacity	%	91.0	%	91.0	TAPPI T425
Stiffness-MD	Gurley (mg)	220	mN	2.2	TAPPI T543

ADHESIVE

Ultra-removable microsphere adhesive designed for paper facers. Adheres to, and removes cleanly from, a variety of substrates. Repositionable. Perfect for kids stickers, forms, and short-term labeling such as price marking, promotions, and logistics.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.4	um(micrometer)	10.8	
Peel - 180 D SS 20 min	lb/inch	.50	grams/25 mm	223.2	CPD-52
Loop Tack Stain Steel	oz/sq inch	12	kg/645 sq mm	.3	CPD-16
Min. App. Temp.	F	20	C	-7	
Service Temp.	F	-10 TO 120	C	-23 TO 49	
FDA Compliance	21 CFR	175.105			

Notes

This adhesive is not intended for layflat applications.

LINER

A white densified kraft sheet 41# (67 g/m²) with excellent point-to-point caliper control.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/24X36-500	40.6	grams/sq meter	66.2	TAPPI T410
Caliper - Average	mil	2.4	um (micrometer)	61.0	TAPPI T411
Opacity	%	60	%	60.0	TAPPI T425
Tear-MD	grams	34	mN	333.4	TAPPI T414
Tear-CD	grams	39	mN	382.5	TAPPI T414
Tensile-MD	lb/inch	40	kN/m	7.0	TAPPI T494
Tensile-CD	lb/inch	17	kN/m	3.0	TAPPI T494
Brightness	%	76	%		TAPPI T452

Issued: 11/22/17

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions (found in the current Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book) in effect at the time of the sale shall control.

La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho. Los Términos y Condiciones vigentes que regulan toda relación comercial de Green Bay Packaging Inc. - Coated Products Operations son los que se encuentran impresos en inglés en el último Libro de Precios. (Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book.)

SPECIALISTS IN COATED SELF-ADHESIVE MATERIALS

ESPECIALISTAS EN MATERIALES AUTO-ADHESIVOS

3250 South Ridge Road • P. O. Box 19017 • Green Bay, WI 54307-9017 • USA

Phone: 001-(920)-337-1800, 800-445-4269, WI: 800-472-4442 • FAX: 001-(920)-337-1797, 800-705-0111