



**054WS0074712NB**

**Item #: S8906760**

54# SEMI GLOSS WET STRNG/747 PERMANENT ADHESIVE/1.2 ML PET NO BACK COAT  
Approximate weight per MMSI: 201 lbs. Standard core size is 3 inches. Total caliper: 4.8 mils +/- 10%

**FACESTOCK**

54# (80 g/m<sup>2</sup>) C1S blue-white semi-gloss. Wet strength makes it stand up to moisture. Ideal for labeling chilled beverages, including beer and wine, or refrigerated foods. Smooth surface enhances print results with flexo, laser and other press types.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Basis Weight	lbs/25X38-500	54	grams/sq meter	79.9	TAPPI T410
Caliper - Average	mil	2.9	um (micrometer)	73.7	TAPPI T411
Gloss	% @ 75 degrees	65	% @ 75 degrees	65.0	TAPPI T480
Opacity	%	85	%	85.0	TAPPI T425
Smoothness (PPS) Print Side	um	1	um	1.0	TAPPI T555
Tensile-MD	lb/inch	30	kN/m	5.3	TAPPI T494
Brightness	%	87	%	87.0	TAPPI T452

**ADHESIVE**

A general purpose, tackified acrylic permanent that displays excellent adhesion over a broad temperature range while providing aggressive performance. Perfect for wine labeling, as it can be used in moist environments. Withstands ice bucket conditions.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper - Calculated	mils	0.7	um(micrometer)	17.3	
Shear (1 x 1/2 x 1 kg)	hours	15	hours	15.0	CPD-55
Peel - 180 D SS 20 min	lb/inch	3.3	grams/25 mm	1473.3	CPD-52
Loop Tack Stain Steel	oz/sq inch	53	kg/645 sq mm	1.5	CPD-16
Loop Tack Glass	oz/sq inch	60	kg/645 sq mm	1.7	CPD-16
Min. App. Temp.	F	0	C	-18	
Service Temp.	F	-65 TO 200	C	-54 TO 93	
FDA Compliance	21 CFR	175.105			

**LINER**

Clear polyester with an excellent surface for die-cutting. Great strength for high speed converting and application.

Test Property	Units	Typical Value	Metric Units	Metric Value	Test Method
Caliper Average (Films)	mils	1.2	um (micrometers)	30.5	ASTM D374
Tensile Film - MD	lb/sq inch	32,000	kg/sq cm	2249.6	ASTM D882
Tensile Film - TD	lb/sq inch	32,000	kg/sq cm	2249.6	ASTM D882
Elongation at Break - MD	%	130	%	130.0	ASTM D882
Elongation at Break - TD	%	100	%	100.0	ASTM D882
Shrinkage-MD	% 30 min @ 302 F	1.5	% 30 min @ 150 C	1.5	ISO 2469
Shrinkage-TD	% 30 min @ 302 F	.4	% 30 min @ 150 C	.4	ISO 2469
Elastic Modulus - MD	lb/sq inch	550,000	kg/sq cm	38665.0	ASTM D882
Elastic Modulus - TD	lb/sq inch	550,000	kg/sq cm	38665.0	ASTM D882
Area Yield	sq in/lb	16,805	sq m/kg	24.0	ASTM E252

Issued: 07/20/17

The information presented in this publication is believed to be accurate and is not intended to constitute a specification. The values given reflect average material characteristics. All statements, technical information and recommendations about Green Bay Packaging Inc. products are based upon tests believed to be reliable, but do not constitute a guarantee or warranty. All products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purpose. No salesperson, representative, or agent of Green Bay Packaging Inc. is authorized to give any guarantee, warranty, or make any representation contrary to the above. The company's standard Terms and Conditions (found in the current Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book) in effect at the time of the sale shall control.

*La información presentada en esta publicación se considera correcta; no debe ser interpretada como una especificación. Los valores dados reflejan las características regulares de los materiales. Todos los informes, fichas técnicas, y recomendaciones de los productos de Green Bay Packaging Inc. están basados en pruebas que se consideran confiables, pero no constituyen ningún tipo de garantía. Todos los productos se venden con el entendimiento de que el comprador ha determinado independientemente la conveniencia de estos productos para su uso final. Ningún vendedor, representante, ni agente de Green Bay Packaging Inc. está autorizado para dar ningún tipo de garantía, ni hacer representación alguna contraria a lo susodicho. Los Términos y Condiciones vigentes que regulan toda relación comercial de Green Bay Packaging Inc. - Coated Products Operations son los que se encuentran impresos en inglés en el último Libro de Precios. (Green Bay Packaging Inc. - Coated Products Operations, Roll Printer Price Book.)*

SPECIALISTS IN COATED SELF-ADHESIVE MATERIALS

ESPECIALISTAS EN MATERIALES AUTO-ADHESIVOS

3250 South Ridge Road • P. O. Box 19017 • Green Bay, WI 54307-9017 • USA  
Phone: 001-(920)-337-1800, 800-445-4269, WI: 800-472-4442 • FAX: 001-(920)-337-1797, 800-705-0111